


## L-Ag5P

CATEGORY	Brazing																						
TYPE	Copper phosphorus silver brazing alloy.																						
APPLICATIONS	Particularly recommended for sanitary and refrigerating equipment. Suitable for working temperatures up to 200°C																						
PROPERTIES	Excelent flowing alloy with high purity offering strong brazing joints. Do not use in a sulphurous environment.																						
CLASSIFICATION	AWS	A 5.8: BCuP-3																					
	EN ISO	1044: CP 104																					
	DIN	8513: L-Ag5P																					
SUITABLE FOR	Copper to copper (without flux). Brass, copper and copper-tin alloys (with flux).																						
APPROVALS	CE approved																						
WELDING POSITIONS:																							
FILLER METAL ANALYSIS %	<table><tr><td>Ag</td><td>Cu</td><td>Si</td><td>P</td></tr><tr><td>5</td><td>89</td><td>0.02</td><td>6</td></tr></table>					Ag	Cu	Si	P	5	89	0.02	6										
Ag	Cu	Si	P																				
5	89	0.02	6																				
MECHANICAL PROPERTIES	<table><tr><td>Heat Treatment</td><td>R<sub>p0,2</sub> (N/mm<sup>2</sup>)</td><td>R<sub>m</sub> (N/mm<sup>2</sup>)</td><td>Weight g/cm<sup>3</sup></td><td>Operating temperature °C</td><td>Impact Energy (J) ISO-V -40°C    -60°C</td><td>Melting range °C</td></tr><tr><td>As brazed</td><td></td><td>250</td><td>8.2</td><td>710</td><td></td><td>645-800</td></tr></table>					Heat Treatment	R <sub>p0,2</sub> (N/mm <sup>2</sup> )	R <sub>m</sub> (N/mm <sup>2</sup> )	Weight g/cm <sup>3</sup>	Operating temperature °C	Impact Energy (J) ISO-V -40°C    -60°C	Melting range °C	As brazed		250	8.2	710		645-800				
Heat Treatment	R <sub>p0,2</sub> (N/mm <sup>2</sup> )	R <sub>m</sub> (N/mm <sup>2</sup> )	Weight g/cm <sup>3</sup>	Operating temperature °C	Impact Energy (J) ISO-V -40°C    -60°C	Melting range °C																	
As brazed		250	8.2	710		645-800																	
BRAZING PARAMETERS / PACKING	<table><tr><td colspan="2">Welding Parameters</td><td>Flame type</td><td>Optimum brazing</td><td colspan="2">Packing</td></tr><tr><td>D (mm)</td><td>Length (mm)</td><td>Adjustment</td><td>Gab (mm)</td><td>kg / tube / carton</td><td>kg spool</td></tr><tr><td>1.5</td><td>500 / 1000</td><td>Neutral</td><td>0.06-0.13</td><td>1 / 5 / 20</td><td>1 till 10</td></tr></table>					Welding Parameters		Flame type	Optimum brazing	Packing		D (mm)	Length (mm)	Adjustment	Gab (mm)	kg / tube / carton	kg spool	1.5	500 / 1000	Neutral	0.06-0.13	1 / 5 / 20	1 till 10
Welding Parameters		Flame type	Optimum brazing	Packing																			
D (mm)	Length (mm)	Adjustment	Gab (mm)	kg / tube / carton	kg spool																		
1.5	500 / 1000	Neutral	0.06-0.13	1 / 5 / 20	1 till 10																		
REDRYING TEMPERATURE	not required																						
OTHER DELIVERY FORMS	Endless wire on spools and customized brazing rings																						